

Description: Bi-colour medium weight flock lined neoprene over natural rubber gloves

- Features & Benefits:
- * Anatomically shaped for comfort
 - * Anti-slip pattern for good grip in wet and dry conditions
 - * Bacteriostatic and fungistatic additives
 - * Chlorinated for improved chemical resistance
 - * Compliant with (EC) No. 1935/2004, EU 10/2011 & BFR XXI (Blue over Yellow)
 - * Ingredients comply with FDA regulations for food contact (Blue only)
 - * Low in soluble proteins
 - * Neoprene over natural rubber
 - * Palm strengthened by special dip for extra protection
 - * Pure cotton lining to absorb perspiration

Applications: Agriculture, Aircraft Industry, Automotive Industry, Chemical Industry, Facility maintenance

Elastomer: Natural/Neoprene blended rubber

Thickness: 0.60 +/- 0.06 mm

Lining: Flocklined

Former: Honeycomb CIH

Exterior: Finished smooth

Cuff Types: Straight

Treatments: Un-chlorinated, Wash, Chlorinated

Colours: Blue on Yellow B4/Y1, Blue on Yellow B5/Y1, Red on Yellow R1/Y1

AQL - Critical: 1.5

Major: 4

CE Certification: Conforms to PPE Regulation EU 2016/425 to(Complex Design) Personal Protective Equipment after assessment against standards EN 374-1:2016+A1:2018, EN 374-5:2016,EN 388:2016+A1:2018 and EN ISO 21420:2020


Conforms to: ASTM D4679 of 2021

| Physical Dimensions: | Size | Palm | Wrist | Cuff | Length |
|----------------------|-------|------|-------|------|--------|
| | 6-6.5 | 198 | 183 | 248 | 300 |
| | 7-7.5 | 208 | 190 | 251 | 300 |
| | 8-8.5 | 215 | 202 | 268 | 300 |
| | 9-9.5 | 235 | 226 | 280 | 300 |
| | XL | 250 | 237 | 293 | 310 |

Circumference in mm, +/- 5 mm Tol. +/- 10 mm

Shelf Life 3 Years

EN 374-4

| Protection against Chemical hazards | Performance | Degradation % |
|--|-------------|---------------|
| EN ISO 374-1/TYPE A | | |
|  * Methanol (A) | Level 2 | 4.9 |
| * Sodium hydroxide 40% (K) | Level 6 | -13.3 |
| * Sulphuric acid 96% (L) | Level 3 | 26.4 |
| * Nitric acid 65% (M) | Level 5 | 21.9 |
| * Acetic acid 99% (N) | Level 2 | 22.7 |
| * Ammonium hydroxide 25% (O) | Level 1 | -12.3 |
| * Hydrogen peroxide 30% (P) | Level 6 | 6.5 |
| * Formaldehyde 37% (T) | Level 6 | -1.6 |
| * Hydrofluoric acid 40% (S) | Level 6 | X |

Note: Printed copies are valid only on the date printed

Printed Date: 28-Nov-2023

Revision:8

Published Date: 28-Nov-2023



No: 400, Deans Road, Colombo 10, Sri Lanka

Phone: +94-0122-683-964

Fax: +94-0122-699-018

E-Mail: postmast@dplgroup.com

Protection against Mechanical hazards **Performance**



- * Abrasion resistance
- * Blade cut resistance
- * Tear resistance
- * Puncture resistance
- * TDM cut resistance

Level 2
Level 1
Level 1
Level 0
X

Protection against Micro-organisms risk **Performance**



- * Protection against bacteria and fungi
- * Protection against viruses

Pass
Pass